

永承地板企業有限公司

新北市板橋區中山路2段386號1樓

以下測試樣品係由客戶所提供及確認：

產品名稱： 綠蒂雅渡假風超耐磨木地板

我們依照客戶的要求,根據客戶送交之樣品進行測試結果如下：

測試要求： 甲醛釋放量 (CNS 11341 條狀地板, 第 5.11 章節)

測試方法： 參考 CNS 11341 條狀地板 (修訂公布日期：103 年 10 月 9 日) 第 6.7 章節

測試結果： --詳 附 頁--

收樣日期： 2017 年 07 月 20 日

測試日期： 2017 年 07 月 20 日 ~ 2017 年 08 月 03 日

Signed for and on behalf of
SGS Taiwan Ltd.

陳志祥
組長



此報告是本公司依照背面所印之通用服務條款所簽發，此條款可在本公司網站 <http://www.sgs.com/en/Terms-and-Conditions.aspx> 閱覽，凡電子文件之格式依 <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx> 之電子文件期限與條件處理，請注意條款有關於責任、賠償之限制及管轄權的約定，任何持有此文件者，請注意本公司製作之結果報告書將僅反映執行時所紀錄且於接受指示範圍內之事實，本公司僅對客戶負責，此文件不妨礙當事人在交易上權利之行使或義務之免除，未經本公司事先書面同意，此報告不可部份複製，任何未經授權的變更、偽造、或曲解本報告所顯示之內容，皆為不合法，違犯者可能遭受法律上最嚴厲之追訴，除非另有說明，此報告結果僅對測試之樣品負責。

測試結果：


測試項目	CAS No	測試結果		定量/偵測極限	單位
		最大值	平均值		
甲醛釋放量	000050-00-0	0.285	0.285	0.0290	mg/L

備註：1. 本報告不得分離，分離使用無效。

2. 若該測試項目屬於定量分析則以「定量極限」表示；若該測試項目屬於定性分析則以「偵測極限」表示。

3. 低於定量極限/偵測極限之測定值以 "N.D."或" 陰性 " 表示。

- 照片 -



照片 A：樣品外觀

-- 以下空白 --

試驗報告



報告編號：HB-18-04360-1

C-18-16918

頁數：1 OF 1

報告日期：107年06月21日

委託單位：永承地板企業有限公司
 地址：新北市板橋區中山路二段386號1樓
 樣品名稱：綠蒂雅渡假風超耐磨木地板 9mm 005 HO-1796
 送驗人員：永承地板企業有限公司(林志芳)
 收件日期：107年06月13日
 試驗日期：107年06月21日
 備註：1. 以上資料由顧客提供(收件及試驗日期除外)

2. 除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果
耐衝擊性	參考 CNS 2215(2017)	無龜裂、剝離、貫穿及裂縫狀態，凹陷直徑 0.0mm

註：本試驗報告取代 HB-18-04360 C-18-16918，原試驗報告作廢，報告修改日期 107 年 08 月 17 日。

規範要求值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA9341182

試驗報告



報告編號：TB-18-03490-1

C-18-09471

頁數：1 OF 1

報告日期：107年06月25日

工程名稱：自測
 承包商：-----
 委託單位：永承地板企業有限公司
 地址：新北市板橋區中山路二段386號1樓
 供料廠商：-----
 樣品名稱：綠蒂雅渡假風超耐磨木地板 9 mm 005 HO-1796
 送驗人員：永承地板企業有限公司-林志芳
 收件日期：107年06月15日
 試驗日期：107年06月15日~107年06月25日
 備註：1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明，此報告結果僅對測試之樣品負責

未經本公司事先書面同意，此報告不可部分複製

3.本樣品由SGS材料暨工程實驗室-台北(申請書號碼：HB-18-04361 C-18-16919，

收件日期：107年06月13日)轉送至本實驗室執行本報告所示之試驗項目。

試驗結果：

試驗項目	試驗結果	CNS 7614(1994) 防焰一級規範值	CNS 7614(1994) 防焰二級規範值	CNS 7614(1994) 防焰三級規範值	試驗方法
火源加熱時間 (sec)	30	-----	-----	-----	CNS 7614(1994) A法
餘焰時間 (sec)	0.0	≤ 1	≤ 5	≤ 5	
餘燼時間 (sec)	0.0	≤ 60	≤ 60	≤ 60	
炭化長度 (cm)	3.5	≤ 5	≤ 10	≤ 15	

註：1.樣品平均厚度 9.0 mm

2.試驗者：陳彥融

3.測試面為正面

4.本試驗之樣品厚度不在TAF認證範圍內，故無法出具TAF標誌之報告。

5.本試驗報告編號取代TB-18-03490 C-18-09471，原試驗報告作廢，報告修改日期107年08月20日。

----- oOo -----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：TB-17-05132

C-17-13099

頁數：1 OF 1

報告日期：106年10月13日


工程名稱：自測
 承包商：-----
 委託單位：永承地板企業有限公司
 地址：新北市板橋區中山路二段386號1F
 供料廠商：-----
 樣品名稱：綠蒂雅渡假風超耐磨木地板
 送驗人員：永承地板企業有限公司-林志芳
 收件日期：106年09月18日
 試驗日期：106年09月18日~106年10月13日
 備註：1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗結果	試驗方法
表面耐磨性-磨耗終點(轉)	22000	CNS 11367(1985)

註：耐磨試驗之片數為1片，研磨紙為AA180，附加於每一磨耗輪之載重為500公克，
 磨耗試驗機的旋轉盤的旋轉速度為60 r/min。

-----oOo-----



本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



綠建材標章證書

綠建材標章證書字號: GBM0101107 (續)

申請廠商: 上采興業股份有限公司

申請人: 王月盈

廠商地址: 高雄市梓官區嘉展路 116 號

產品名稱: 普通合板

產品型號: BBK-P17.548(17.5mm 7層)F1、BBK-P14.548(14.5mm 7層)F1、
BBK-P11.548(11.5mm 7層)F1、BBK-P8.548(8.5mm 5層)F1、
BBK-P6.548(6.5mm 5層)F1

生產廠址: 高雄市梓官區興寶里嘉展路 116 號

有效期限: 自 105 年 2 月 26 日起至 108 年 2 月 25 日止

合格項目: 健康綠建材(E2)

試驗項目: 甲醛(HCHO) 揮發量: 未測出 (低於偵測極限值 0.05 mg/m³ · hr)
總揮發性有機物(TVOC) 揮發量: 未偵測出 (低於偵測極限
值 0.05 mg/m³ · hr)

Green Building
標章

內政部 部長

健康
Healthy



中華民國 105 年 5 月 7 日